



Natural Stone, Beautiful Home

Technical specification of Creggaun Sandstone

1. Water Absorption % by Weight **1.90**
(ASTM C - 97)

2. Density **2.67**
(ASTM C - 97)

3. Wetting & Drying Test:
(BS 680 Pt 2)

No signs of de-lamination / splitting along the edges when examined through a lens, nor of flaking of the surface.

4. Sulphuric Acid Immersion Test:
(BS 680 Pt2)

No signs of de-lamination along the edges when examined through a lens, nor of swelling or softening or flaking of the surface and no gaseous evolution during immersion.